

tyco



OVER 110 YEARS OF QUALITY & SERVICE IN THE HOSE INDUSTRY

MANUFACTURER OF MUNICIPAL, FORESTRY AND INDUSTRIAL HOSE

DRAFTEX[®]



NIEDNER IS AN ISO9001:2000 CERTIFIED COMPANY BY UL REGISTRAR
SUPERIOR PRODUCTS THAT SUPPORT YOU IN **SAVING LIVES**

www.niedner.com

DRAFTEX®

An extremely lightweight suction hose, the DRAFTEX® single jacket construction uses 100% spun polyester combined with a helical interior reinforcement. It is lined with TPU elastomer and encapsulated with red DRAFTKOTE™ to enhance durability. With a service test pressure rating of 300 PSIG (2100 kPa), DRAFTEX® is designed for Forest Service use with portable pumps as well as other pump applications. Patent No. 2168497.

- Construction: Circular woven, single jacket 100% virgin spun polyester, combined with a helical interior reinforcement.
- Tube: Extruded T.P.U. elastomer - Ozone and age resistant.
- Standard lengths: 6', 8' and 10' (1.8, 2.4 and 3 m)
- Jacket treatment: DRAFTKOTE™ encapsulation (in red). Provides a measurable increase in abrasion resistance as well as resistance to acids, oils, chemicals and salt water.

How to specify DRAFTEX®

- The hose shall be a single jacket construction of 100% virgin spun polyester, DRAFTKOTE™ treated, combined with a special helical interior reinforcement.
- There shall be a minimum of 12.5 filler yarns per inch in the jacket.
- The thickness of the lining shall be 0.030" (762 µm) minimum and it shall be constructed of extruded T.P.U. elastomer.
- The hose shall be treated with DRAFTKOTE™ elastomer which shall completely encapsulate the jacket fibers and not merely surface coat the jacket.
- The hose service temperature range shall be -60°F to 140°F (-51°C to 60°C).
- FM abrasion test of 3,000 cycles minimum.
- At 600 PSIG (4200 kPa), its elongation shall not exceed 6% of the initial hose length, it shall not warp more than 10 inches (25 cm) and should not rise from the test table.
- The hose shall not twist more than 10 turns per 100 ft (30,5 m) while at 450 PSIG (3150 kPa).
- Minimum service test pressure of 300 PSIG (2100 kPa).
- Minimum proof test pressure of 600 PSIG (4200 kPa).
- Minimum straight burst test pressure of 900 PSIG (6300 kPa).
- The hose while curved to a radius of 27" (69 cm) shall not burst at less than 900 PSIG (6300 kPa).
- Withstands vacuum of 25 inches of mercury (84,7 kPa).

DRAFTEX® PHYSICAL PROPERTIES

Hose size	Spec number	Coupling bowl size	Weight / 10 ft (3,1 m) coupled	Minimum kink burst test pressure
1 1/2 " (38 mm)	3265	1 13/16" (46,0 mm)	4.5 lbs (2,0 kg)	500 PSIG (3500 kPa)
2 " (51 mm)	3270	2 3/8" (60,3 mm)	5.0 lbs (2,3 kg)	500 PSIG (3500 kPa)

For more information please call your authorized dealer.

NIEDNER
ISO 9001 REGISTERED

1-800-567-2703
sales.niedner@tycoint.com



675 Merrill St. Coaticook, QC Canada J1A 2S2
E-mail: sales.niedner@tycoint.com Web: www.niedner.com



PO Box 38, Norton, VT USA 05907
Tel.: (819) 849-2751 1-800-567-2703 Fax.: (819) 849-7539